

**Amendments to the Specification:**

Please replace the paragraph beginning on page 17, line 3, with the following rewritten paragraph:

-- To improve colorant fade, UV absorbers, radical quenchers or antioxidants may also be added to the image-receiving layer as is well known in the art, although the use of UV absorbers is excluded in a claim to an image-receiving layer consisting essentially of stabilizer particles for improved colorant fade. Other additives include pH modifiers, adhesion promoters, rheology modifiers, surfactants, biocides, lubricants, dyes, optical brighteners, matte agents, antistatic agents, etc. In order to obtain adequate coatability, additives known to those familiar with such art such as surfactants, defoamers, alcohol and the like may be used. A common level for coating aids is 0.01 to 0.30 % active coating aid based on the total solution weight. These coating aids can be nonionic, anionic, cationic or amphoteric. Specific examples are described in MCCUTCHEON's Volume 1: Emulsifiers and Detergents, 1995, North American Edition. --

Please do  
not enter  
PR 7/28/04